


Outstanding thermal
performance and appearance



Soltis

Perform 92

Main applications

Facade blinds, veranda and glass roof blinds, drop-arm awnings and shade sails



■ Keeps out up to **97%** of the heat

Soltis Perform 92 acts like a **heat shield**.

Its micro-vents filter the heat, reducing a building's energy costs.

■ Glare control

is combined with excellent transparency for better user comfort. Soltis Perform 92's thermal and optical performance earns building certification program points (LEED, BREEAM, Minergie, HQE, etc.).

■ High colour resistance over time

Colour is preserved even after several years of exposure (according to the ISO 105 A02 scale).

4x
MORE RESISTANCE
than a standard product

The Soltis Perform 92 fabric's resistance delivers longer durability to provide you with better performance over a longer period of time.

2x
THINNER
than a standard product

Reduced thickness for enhanced facade appearance and reduced bulk, even with extended blind heights.

Soltis Perform 92 - 3 key properties



Dimensional stability
thanks to Précontraint® technology



Easy to clean




UV resistant



Soltis

Perform 92




new Snow white 177 cm — 267 cm

92-50690




White 177 cm — 267 cm

92-2044




Alu/White 177 cm — 267 cm

92-2051



Alu/Oat 177 cm — 267 cm

92-2046




Alu/Alu 177 cm — 267 cm

92-2048




Alu/ Medium grey 177 cm — 267 cm

92-2074



Alu/Anthracite 177 cm

92-2068




Gold 177 cm

92-50273



Copper 177 cm

92-50274



Beaten metal 177 cm — 267 cm

92-2045



Bronze 177 cm — 267 cm

92-2043



Beetle 177 cm

92-2149




new Deep black 177 cm—267 cm


92-51176



Champagne 177 cm — 267 cm 92-2175




new Quartz 177 cm — 267 cm 92-50303



new Shea 177 cm — 267 cm 92-50843



Pepper 177 cm — 267 cm 92-2012




Hemp 177 cm — 267 cm 92-50265



Sandy beige 177 cm — 267 cm 92-2135




Havana-Brown 177 cm 92-50266



new Taupe 177 cm — 267 cm 92-50850



Cloud 177 cm — 267 cm 92-50272



Boulder 177 cm — 267 cm 92-2171



Concrete 177 cm — 267 cm 92-2167




new Dark grey 177 cm — 267 cm 92-51177



new Celestial grey 177 cm 92-51178



Anthracite 177 cm — 267 cm 92-2047



Moss green 177 cm 92-2158



new Green-grey 177 cm 92-51179



new Tennis green 177 cm 92-8056



new Brick 177 cm 92-51180



new Deep red 177 cm 92-51181



Buttercup 177 cm

92-2166



Lagoon 177 cm

92-2160



Orange 177 cm

92-8204



Aniseed 177 cm

92-2157



new Deep blue 177 cm

92-51182



Red 177 cm

92-8255

new Colours Collection

TERRACE



INTERIOR
BLINDS



EXTERIOR
BLINDS



A range of colours to match all of your projects


The new Soltis Perform 92 range features colours designed by our design office to complement the building's entire environment (joinery, openings and facades). The colours present tones that match the most common colours (RAL and NCS references).



Download
our RAL and NCS
colour correspondence.




■ Colours coordinated with Soltis Horizon 86



■ Exclusive Précontraint® technology

This unique worldwide patented technology consists of maintaining the composite in bi-axial tension throughout the entire manufacturing cycle. It gives our materials outstanding performance, allowing them to surpass market standards in terms of dimensional stability, mechanical strength, coating thickness and flatness.



High tenacity polyester micro-cable reinforcement	①	Superior resistance to elongation and tearing
Coating under bi-axial tension, exerted in warp and weft	②	No deformation during implementation and use
Superior coating at the crest of the wires and anti-fouling surface treatment	③	Superior aesthetic and mechanical durability
Extreme flatness and low thickness	④	Smooth, easy to clean surface with small footprint and easy winding

■ Solar and light properties (according to EN 14501)

		Width (in cm)		TS	RS	AS	TV n-h	ISO 52022-3* Glazing D	
		177	267					g_{tot}^e	g_{tot}^i
92-2012		•	•	7	30	63	6	0.04	0.24
92-2043		•	•	4	13	83	4	0.04	0.28
92-2044		•	•	19	68	13	17	0.07	0.11
92-2045		•	•	4	35	61	4	0.03	0.22
92-2046	A	•	•	12	46	42	10	0.05	0.18
92-2046	B	•	•	12	63	25	10	0.05	0.14
92-2047		•	•	5	8	87	5	0.04	0.28
92-2048		•	•	8	46	46	8	0.04	0.18
92-2051	A	•	•	12	49	39	11	0.06	0.17
92-2051	B	•	•	12	70	18	11	0.05	0.10
92-2068	A	•		4	34	62	4	0.03	0.22
92-2068	B	•		4	8	88	4	0.04	0.28
92-2074	A	•	•	4	37	59	4	0.03	0.21
92-2074	B	•	•	4	25	71	4	0.03	0.24
92-2135		•	•	11	46	43	8	0.04	0.19
92-2149		•		5	16	79	4	0.04	0.27
92-2157		•		15	51	34	10	0.05	0.20
92-2158		•		7	28	65	5	0.03	0.24
92-2160		•		11	36	53	5	0.04	0.24
92-2166		•		21	54	25	17	0.07	0.19
92-2167		•	•	6	19	75	5	0.04	0.26

		Width (in cm)		TS	RS	AS	TV n-h	ISO 52022-3* Glazing D	
		177	267					g_{tot}^e	g_{tot}^i
92-2171		•	•	8	41	51	6	0.04	0.20
92-2175		•	•	19	65	16	17	0.07	0.14
new 92-8056		•		2	10	88	2	0.03	0.28
92-8204		•		21	45	34	11	0.06	0.23
92-8255		•		12	28	60	4	0.05	0.27
92-50265		•	•	9	49	42	6	0.04	0.18
92-50266		•		4	19	77	4	0.03	0.26
92-50272		•	•	12	55	33	9	0.05	0.16
92-50273		•		8	42	50	5	0.04	0.21
92-50274		•		8	35	57	4	0.04	0.24
new 92-50303		•	•	15	63	22	10	0.05	0.15
new 92-50843		•	•	13	62	25	10	0.05	0.14
new 92-50850		•	•	5	31	64	3	0.03	0.23
new 92-50690		•	•	17	73	10	15	0.06	0.10
new 92-51176		•	•	3	5	92	3	0.03	0.29
new 92-51177		•	•	3	18	79	3	0.03	0.26
new 92-51178		•		5	20	75	4	0.03	0.26
new 92-51179		•		6	29	65	4	0.03	0.24
new 92-51180		•		6	27	67	3	0.03	0.26
new 92-51181		•		4	17	79	3	0.03	0.28
new 92-51182		•		8	26	66	4	0.03	0.27

TS: Solar Transmission in %

RS: Solar Reflection in %

AS: Solar absorption in %

TS + RS + AS = 100% of the incident energy

TV n-h: Normal Visible light transmission - hemispherical in %

A: Aluminium surface exposed to the sun

B: Coloured surface exposed to the sun

g_{tot}^e : External Solar Factor

g_{tot}^i : Indoor Solar Factor

* Detailed
ISO 52022-3 method

Takes into account the spectral values of glazing transmission and reflection + blind complex for calculating the solar factor g_{tot}.
Type "D" glazing: insulating double glazing with low emissivity on surface 2 (4 + 16 + 4; Argon filling) g = 0.32 - U = 1.1



Soltis

Perform 92

	■ Technical properties	Standards
Openness factor	4%	
Weight	420 g/m ² - 12.3 oz/yd ²	EN ISO 2286-2
Thickness	0.45 mm	
Width	177 cm - 267 cm - 69.6 in - 105.1 in	
	■ Roll length	
Standard piece size: 177 cm - 69.6 in	50 lm - 54.6 yds	
Standard piece size: 267 cm - 105.1 in	40 lm - 43.7 yds	
	■ Physical properties	
Breaking resistance (warp/weft)	310/210 daN/5 cm	EN ISO 1421
Tear resistance (warp/weft)	45/20 daN	DIN 53.363
	■ Reaction to fire	
Rating	M1/NFP 92-507 — B1/4102-1 — BS 7837 — BS 5867 — CSFMT19 — Class A/ASTM E84 Schwerbrennbar-Q1-Tr1/ONORM A 3800-1 — Class 1/EN 13773 — M1/UNE 23.727-90 VKF 5.3/SN 198898 — 1530.3/AS/NZS — G1/GOST 30244-94 — Method 1/NFPA 701 Class 1/UNI 9177-87	
Euroclass	B-s2,d0	EN 13501-1
	■ Management system	
Quality		ISO 9001
Environment		ISO 14001
Energy		ISO 50001
	■ Certifications, labels, guarantees	
Précontraint® Technology 5 year warranty	       	1
	■ Tools and services	
ACV and FDES available on request Tool for evaluating the energy savings that can be achieved with Soltis solar protection: SOLTISSIM. Contact your Serge Ferrari representative. ¹ Logo «+=0»: summarises the Serge Ferrari Group's commitment to CSR, to align economic performance and positive impact. Find out about our concrete actions in our CSR report 2021		

The technical characteristics listed are average values with a tolerance of +/- 5%.

Purchasers of our products are responsible for their application or transformation with regard to any third party rights. Purchasers of our products are also responsible for their implementation and installation in compliance with the destination country's best practices and safety rules. Contractual guarantees are included in the terms of the guarantee.

The values mentioned in this document are based on test results in compliance with study practice. These are provided as indications so that customers can obtain optimal performance from using our products. These are subject to technical improvements and we reserve the right to change specifications at any time. Purchasers of our products are responsible for asserting that the data presented above is in compliance with the validity of the above data.